

**Report Date:** August 12, 2020

**Report #:** 25501A-12-08-2020

**Client:** 510 2nd Ave S  
Twin Falls, ID, USA  
83301

**Test:** AATCC TM-104 Colorfastness

**Test Product:** Pear Blossom Room & Linen Spray

**Lab Code #:** 20-0282

**Test Fabrics:**

Black Rayon

White Rayon

Polished Cotton

Silk

Leather


Pleather

Carpet (Almond white, Nylon 6,6 tufted cut pile, no stain repellent treatment)

**Summary of Method:**

This test method is designed to evaluate the colorfastness of dyed, printed or otherwise colored textile fabrics when spotted with the test liquid. The test method does not determine whether the discoloration is removable. The test specimen is spotted with 0.15 mL of the test product on selected fabrics and evaluation is made of change of color, after wetting and after drying using the AATCC Gray Scale for Color Change.

On this scale, 5 indicates that next to no color was lost, and 1 indicates that most color was lost.



*This report shall not be reproduced except in full without the approval of Dell Tech Laboratories  
Results, Opinions & Interpretations relate only to the items tested and the samples as received.*

*Testing performed at Dell Tech Laboratories – 1331 Hyde Park Rd., #3, London, ON, Canada, N6H 5M5 – T:519-858-5021 - [www.delltech.com](http://www.delltech.com)*

**Results:**

<b>Average Gray Scale Color Change Rating</b>		
<b>Fabric</b>	<b>wet</b>	<b>dry</b>
Black Rayon	5.0	5.0
White Rayon	2.5	3.5
Polished Cotton	5.0	5.0
Silk	4.0	5.0
Leather	3.5	5.0
Pleather	2.5	4.0
Carpet (Almond white, Nylon 6,6 tufted cut pile, no stain repellent treatment)	5.0	5.0

**Conclusion:**
















Under the conditions if this test Pear Blossom Room & Linen Spray was observed on:

- Black Rayon to result in no color change when wet and no color change when dry.
- White Rayon to result in moderate color change when wet and minor color change when dry.
- Polished Cotton to result in no color change when wet and no color change when dry.
- Silk to result in slight color change when wet and no color change when dry.
- Leather to result in minor color change when wet and no color change when dry.
- Pleather to result in moderate color change when wet and slight color change when dry.
- Carpet (Almond white, Nylon 6,6 tufted cut pile, no stain repellent treatment) to result in no color change when wet and no color change when dry.

**Tested by:**   
 Dana Mladin, Lab Technician

**Approved by:**   
 Jennifer Grant, President

# Photos

Substrate	Before	After 2 minutes (wet)	After 24 hours (dry)
Black Raylon			
White Raylon			
Polish Cotton			
Silk			
Lether			
Plether			
Carpet	